



---

## CIMWD-122 Syllabus

### *Gas Tungsten Arc Welding – Steel & Stainless Steel, Vertical*

---

#### Recommended Textbook:

Welding: Principles and Applications 8<sup>th</sup> Edition

#### Course Description:

Covers theory and operation of gas tungsten arc welding. Emphasizes proper safety protocols and vertical welding position using mild steel and stainless steel.

#### Course Topics

1. Vertical welding position on steel.
2. Vertical welding position on stainless steel.

#### Learning Objectives

1. Demonstrate the proper welding technique in vertical position with steel.
2. Demonstrate the proper welding technique in vertical position with stainless steel.
3. \*Perform welds using proper preparation and welding technique for a given weldment.

#### Competency-Based Education

The Welding Program at Henry Ford College uses a system of learning called Competency-Based Education (CBE). This competency-based welding program is centered on teaching specific job skills required in industry and mastery of these skills.

CBE is a very personalized teaching system that has the following characteristics:

- Ongoing Program
- Open entry - flexible schedule
- Credit granted for work completed
- Evaluation (grades) based on performance
- Fixed content in each course
- Variety of student levels served in each class
- Work at your own pace
- Live or taped lectures and demonstrations





---

## CIMWD-122 Syllabus

### *Gas Tungsten Arc Welding – Steel & Stainless Steel, Vertical*

---

This competency-based program has several very important benefits for you:

- You will be given a list of the skills and knowledge needed to complete the program successfully.
- Your performance will not be compared to that of other students, but to a fixed standard, which has been set for the program.
- If you have already acquired certain skills required for this program, you may simply demonstrate this and begin focusing your attention on new skills.
- You will be able to review learning materials several times in order to attain the skill or knowledge.
- If you are able to attain the skills easily, you may progress through the program faster than the average person. If you progress through the program faster than average, you can graduate in a shorter time frame.

#### **What's Required of You:**

For this system to work, you will be expected to:

1. Assume the responsibility for your own learning. Your instructor will give you assistance, but the actual responsibility for learning rests with you, the student.
2. Utilize the materials provided for you. The program's resources have been carefully chosen and developed to help you learn.
3. Devote your energy to attaining the skills and knowledge required for your program.

#### **The Instructor's Role:**

The instructors in HFC's Welding Program work with students individually and guide them through the learning process with the help of many different learning resources. In CBE, instructors are often referred to as learning managers because they manage the activities in the program and facilitate the learning process. If you are having difficulty, you should go to your instructor with your problem. The instructor's goal is to find the most effective way to help you learn the tasks in the program.

#### **How your grade is computed in this program:**

If your class is a designated lecture module, your grade will be based off of an exit quiz. When a passing grade is complete, you will be able to move on to the next module.

If this class is a designated lab module, your grade will be based off of a grading matrix. You will evaluate your competencies along with the instructor. You will need a 3-ring binder to keep the finished and signed grading sheets. Those will be turned in when all projects are finished for the module your taking. The final grade will be entered when these are reviewed.





## CIMWD-122 Syllabus

### *Gas Tungsten Arc Welding – Steel & Stainless Steel, Vertical*

#### ***Welding Technology Grading Checklist***

Check	Criteria	Points
	Safety (10 points)	
	PPE	
	Equipment in working order	
	Lab rules followed	
	Work areas cleaned and tools returned	
	Welding, Cutting, & Fabrication Set-Up (10 points)	
	Welding machine set correctly	
	Cutting machines set correctly	
	Fabrication machines set correctly	
	Followed Instructions (10 points)	
	Parts cut to correct size	
	Joints assembled correctly	
	Position of weld was correct	
	Correct filler metal was used	
	Visual Inspection of weld (20 points)	
	Bead width	
	Welding angle	
	Arc gap if applicable	
	Porosity	
	Fillet weld size if applicable	
	Groove weld under fill	
	Joint penetration	
	Incomplete fusion	
	Cracks	
	Cold lap	
	Undercut	
	Arc strikes	
	Fillet weld contour if applicable	
	Inclusions	
	Groove weld height (overfill)	





## CIMWD-122 Syllabus

### *Gas Tungsten Arc Welding – Steel & Stainless Steel, Vertical*

#### Corrective Action Taken:

---



---



---



---



---



---



---

Student: \_\_\_\_\_ Instructor: \_\_\_\_\_

#### Grading Scale:

- A+ = 100-98
- A = 97-93
- A- = 92-90
- B+ = 89-87
- B = 86-83
- B- = 82-80
- C+ = 79-77
- C = 76-73
- C- = 72-70
- D+ = 69-67
- D = 66-63
- D- = 62-60
- E = 59-below

#### Chapters:

16, 17, 22, 23, 25

#### Estimated Time for Projects:

- Project 1: 4 hrs
- Project 2: 4 hrs
- Project 3: 4 hrs
- Project 4: 5 hrs
- Project 5: 5 hrs
- Project 6: 5 hrs





## CIMWD-122 Syllabus

### Gas Tungsten Arc Welding – Steel & Stainless Steel, Vertical

UNLESS OTHERWISE SPECIFIED:	DRAWN	NAME	DATE	TITLE: <b>CIMWD-122 Project 1</b>			
DIMENSIONS ARE IN INCHES	CHECKED						
TOLERANCES:	ENG APPR.			SIZE	DWG. NO.	REV	
FRACTIONAL ±	MFG APPR.			<b>Part 9 1 8 line Vert</b>			
ANGULAR: MACH ± BEND ±	Q.A.			SCALE: 1:2	WEIGHT:	SHEET 1 OF 1	
TWO PLACE DECIMAL ±	COMMENTS:						
THREE PLACE DECIMAL ±	INTERPRET GEOMETRIC TOLERANCING PER:						
	MATERIAL						
	FINISH						
	DO NOT SCALE DRAWING						
	APPLICATION						
	USED ON						

**PROPRIETARY AND CONFIDENTIAL**  
 THE INFORMATION CONTAINED IN THIS DOCUMENT IS THE PROPERTY OF  
 SOLIDWORKS CORPORATION.  
 NO PART OF THIS DOCUMENT IS TO BE REPRODUCED OR TRANSMITTED IN ANY FORM OR BY ANY MEANS, ELECTRONIC OR MECHANICAL, INCLUDING PHOTOCOPYING, RECORDING, OR BY ANY INFORMATION STORAGE AND RETRIEVAL SYSTEM, WITHOUT THE WRITTEN PERMISSION OF SOLIDWORKS CORPORATION.  
 <INSERT COMPANY NAME HERE> IS PROHIBITED.

**SolidWorks Student Edition.**  
**For Academic Use Only.**





## CIMWD-122 Syllabus

### *Gas Tungsten Arc Welding – Steel & Stainless Steel, Vertical*

#### ***Welding Procedure Specification***

WPS Name	CIMWD-122 Project 1
----------	---------------------

Weld Type	Square Groove
Welding Process	GTAW
Position	Vertical
Material	1/8" Steel
Joint Type	Butt
Backing Option	PJP
Backing Material	

Polarity	DC+
Electrode	ER70s-6
Transfer Mode	
Tungsten Electrode	2% Ceriated
Shielding Gas	100% Argon
Flow Rate	25 cfh
Cup Size	

#### ***Welding Procedure***

Weld Layers	Pass No.	Process	Filler Metal Classification	Filler Metal Diameter in (mm)	Current Amps	Current Type and Polarity	Wire Feed Speed	Volts	Remarks
Stringer	Butt	GTAW	ER-70s-6	1/16"	120a	DC+			

Technique:  
Butt Joint single pass weld in vertical up





---

## **CIMWD-122 Syllabus**

### *Gas Tungsten Arc Welding – Steel & Stainless Steel, Vertical*

---

Heat Treatment:

Preheat Temperature-

Post Heat Temperature-

Interpass Temperature-

Stress Relieving-

Additional Notes:

Show the instructor progress every 30 minutes minimum.





# CIMWD-122 Syllabus

## Gas Tungsten Arc Welding – Steel & Stainless Steel, Vertical

UNLESS OTHERWISE SPECIFIED:	DRAWN	CHECKED	ENG APPR.	MFG APPR.	Q.A.	COMMENTS:	NAME	DATE
DIMENSIONS ARE IN INCHES								
TOLERANCES:								
FRACTIONAL ±								
ANGULAR: MACH ±								
BEND ±								
TWO PLACE DECIMAL ±								
THREE PLACE DECIMAL ±								
INTERPRET GEOMETRIC TOLERANCING PER:								
MATERIAL								
FINISH								
DO NOT SCALE DRAWING								

PROPRIETARY AND CONFIDENTIAL

THE INFORMATION CONTAINED IN THIS DRAWING IS THE PROPERTY OF THE M-SAMC. IT IS TO BE USED ONLY FOR ACADEMIC PURPOSES. ANY REPRODUCTION OR DISTRIBUTION OF THIS DRAWING WITHOUT THE WRITTEN PERMISSION OF THE M-SAMC IS PROHIBITED.

**SolidWorks Student Edition.**  
**For Academic Use Only.**

SIZE DWG. NO. REV

**Aart 7 1 8TH vert**

SCALE: 1:2 WEIGHT: SHEET 1 OF 1







## CIMWD-122 Syllabus

### *Gas Tungsten Arc Welding – Steel & Stainless Steel, Vertical*

#### ***Welding Procedure Specification***

WPS Name	CIMWD-122 Project 2
----------	---------------------

Weld Type	Fillet
Welding Process	GTAW
Position	Vertical
Material	1/8" Steel
Joint Type	Lap
Backing Option	
Backing Material	

Polarity	DC+
Electrode	ER70s-6
Transfer Mode	
Tungsten Electrode	2% Ceriated
Shielding Gas	100% Argon
Flow Rate	25 cfh
Cup Size	

#### ***Welding Procedure***

Weld Layers	Pass No.	Process	Filler Metal Classification	Filler Metal Diameter in (mm)	Current Amps	Current Type and Polarity	Wire Feed Speed	Volts	Remarks
Stringer	Lap	GTAW	ER-70s-6	1/16"	120a	DC+			

Technique: Lap Joint single pass weld in vertical up
---





---

## **CIMWD-122 Syllabus**

### *Gas Tungsten Arc Welding – Steel & Stainless Steel, Vertical*

---

Heat Treatment:

Preheat Temperature-

Post Heat Temperature-

Interpass Temperature-

Stress Relieving-

Additional Notes:

Show the instructor progress every 30 minutes minimum.





# CIMWD-122 Syllabus

## Gas Tungsten Arc Welding – Steel & Stainless Steel, Vertical

**NOTE: SHEAR CUT  
TACK WITH GMAW  
WELDED IN MODULE  
YOU ARE PARTICIPATING IN NEXT**

UNLESS OTHERWISE SPECIFIED:		NAME	DATE
DIMENSIONS ARE IN INCHES		J. SIBERT	2/19/2015
TOLERANCES:			
FRACTIONAL: ±			
ANGULAR: MACH: ±	BEND: ±		
TWO PLACE DECIMAL: ±			
THREE PLACE DECIMAL: ±			
INTERPRET GEOMETRIC TOLERANCING PER:	Q.A.		
MATERIAL	COMMENTS:		
FINISH			
DO NOT SCALE DRAWING			

**PROPRIETARY AND CONFIDENTIAL**

**SolidWorks Educational Edition.**

**For Instructional Use Only.**

THE INFORMATION CONTAINED IN THIS DRAWING IS THE PROPERTY OF SOLIDWORKS CORPORATION. IT IS TO BE USED ONLY FOR THE PURPOSES SPECIFIED HEREIN. ANY REPRODUCTION OR TRANSMISSION OF THIS DRAWING WITHOUT THE WRITTEN PERMISSION OF SOLIDWORKS CORPORATION IS PROHIBITED.

SIZE DWG. NO. REV

**A PART 8 0**

SCALE: 1:2 WEIGHT: SHEET 1 OF 1





## CIMWD-122 Syllabus

### *Gas Tungsten Arc Welding – Steel & Stainless Steel, Vertical*

#### ***Welding Procedure Specification***

WPS Name	CIMWD-122 Project 3
----------	---------------------

Weld Type	Fillet
Welding Process	GTAW
Position	Vertical
Material	1/8" Steel
Joint Type	Tee
Backing Option	
Backing Material	

Polarity	DC+
Electrode	ER70s-6
Transfer Mode	
Tungsten Electrode	2% Ceriated
Shielding Gas	100% Argon
Flow Rate	25 cfh
Cup Size	

#### ***Welding Procedure***

Weld Layers	Pass No.	Process	Filler Metal Classification	Filler Metal Diameter in (mm)	Current Amps	Current Type and Polarity	Wire Feed Speed	Volts	Remarks
Stringer	Tee	GTAW	ER-70s-6	1/16"	120a	DC+			

Technique: Tee Joint single pass weld in vertical up
---





---

## **CIMWD-122 Syllabus**

### *Gas Tungsten Arc Welding – Steel & Stainless Steel, Vertical*

---

Heat Treatment:

Preheat Temperature-

Post Heat Temperature-

Interpass Temperature-

Stress Relieving-

Additional Notes:

Show the instructor progress every 30 minutes minimum.





# CIMWD-122 Syllabus

## Gas Tungsten Arc Welding – Steel & Stainless Steel, Vertical

UNLESS OTHERWISE SPECIFIED:		NAME	DATE
DIMENSIONS ARE IN INCHES			
TOLERANCES:			
FRACTIONAL: ±			
ANGULAR: MACH ± BEND ±			
TWO PLACE DECIMAL ±			
THREE PLACE DECIMAL ±			
INTERPRET GEOMETRIC TOLERANCING PER:			
MATERIAL			
FINISH			
DO NOT SCALE DRAWING			

**PROPRIETARY AND CONFIDENTIAL**  
THE INFORMATION CONTAINED IN THIS DRAWING IS THE PROPERTY OF THE COMPANY. IT IS TO BE USED ONLY FOR THE PROJECT AND NOT BE REPRODUCED OR TRANSMITTED IN ANY FORM OR BY ANY MEANS, WITHOUT THE WRITTEN PERMISSION OF THE COMPANY.

**SolidWorks Student Edition.**  
**For Academic Use Only**

<INSERT COMPANY NAME HERE> IS PROHIBITED.

REV

**Part 9 1 8 line Vert**

SCALE: 1:2 WEIGHT: SHEET 1 OF 1





## CIMWD-122 Syllabus

### *Gas Tungsten Arc Welding – Steel & Stainless Steel, Vertical*

#### ***Welding Procedure Specification***

WPS Name	CIMWD-122 Project 4
----------	---------------------

Weld Type	Square Groove
Welding Process	GTAW
Position	Vertical
Material	1/8" Stainless Steel
Joint Type	Butt
Backing Option	
Backing Material	

Polarity	DC+
Electrode	308
Transfer Mode	
Tungsten Electrode	2% Ceriated
Shielding Gas	100% Argon
Flow Rate	25 cfh
Cup Size	

#### ***Welding Procedure***

Weld Layers	Pass No.	Process	Filler Metal Classification	Filler Metal Diameter in (mm)	Current Amps	Current Type and Polarity	Wire Feed Speed	Volts	Remarks
Stringer	Butt	GTAW	308	1/16"	75a	DC+			

Technique: Butt Joint single pass weld in vertical up
--





---

## **CIMWD-122 Syllabus**

### *Gas Tungsten Arc Welding – Steel & Stainless Steel, Vertical*

---

Heat Treatment:

Preheat Temperature-

Post Heat Temperature-

Interpass Temperature-

Stress Relieving-

Additional Notes:

Show the instructor progress every 30 minutes minimum.








# CIMWD-122 Syllabus

## Gas Tungsten Arc Welding – Steel & Stainless Steel, Vertical



DRAWN		NAME		DATE		TITLE:		REV	
CHECKED						CIMWD-122 Project 5		Part 7 1 8TH vert	
ENG APPR.								SIZE DWG. NO.	
MFG APPR.								Scale 7 1 8TH vert	
Q.A.								SCALE: 1:2 WEIGHT: SHEET 1 OF 1	
COMMENTS:								1	
UNLESS OTHERWISE SPECIFIED:								2	
DIMENSIONS ARE IN INCHES								3	
TOLERANCES:								4	
FRACTIONAL ±								5	
ANGULAR: MACH ± BEND ±									
TWO PLACE DECIMAL ±									
THREE PLACE DECIMAL ±									
INTERPRET GEOMETRIC TOLERANCING PER:									
MATERIAL									
FINISH									
DO NOT SCALE DRAWING									
APPLICATION									
USED ON									
PROPRIETARY AND CONFIDENTIAL									
THE INFORMATION CONTAINED IN THIS									
DRAWING IS THE PROPERTY OF									
SOLIDWORKS CORPORATION									
AND IS TO BE USED ONLY FOR									
ACADEMIC PURPOSES. ANY									
REPRODUCTION OR TRANSMISSION									
WITHOUT THE WRITTEN PERMISSION									
OF SOLIDWORKS CORPORATION IS									
PROHIBITED.									





## CIMWD-122 Syllabus

### *Gas Tungsten Arc Welding – Steel & Stainless Steel, Vertical*

#### **Welding Procedure Specification**

WPS Name	CIMWD-122 Project 5
----------	---------------------

Weld Type	Fillet
Welding Process	GTAW
Position	Vertical
Material	1/8" Stainless Steel
Joint Type	Lap
Backing Option	
Backing Material	

Polarity	DC+
Electrode	308
Transfer Mode	
Tungsten Electrode	2% Ceriated
Shielding Gas	100% Argon
Flow Rate	25 cfh
Cup Size	

#### **Welding Procedure**

Weld Layers	Pass No.	Process	Filler Metal Classification	Filler Metal Diameter in (mm)	Current Amps	Current Type and Polarity	Wire Feed Speed	Volts	Remarks
Stringer	Lap	GTAW	308	1/16"	75a	DC+			

Technique:  
Butt Joint single pass weld in vertical up





---

## **CIMWD-122 Syllabus**

### *Gas Tungsten Arc Welding – Steel & Stainless Steel, Vertical*

---

Heat Treatment:

Preheat Temperature-

Post Heat Temperature-

Interpass Temperature-

Stress Relieving-

Additional Notes:

Show the instructor progress every 30 minutes minimum.





# CIMWD-122 Syllabus

## Gas Tungsten Arc Welding – Steel & Stainless Steel, Vertical

DRAWN	CHECKED	ENG APPR.	MFG APPR.	Q.A.	COMMENTS:	NAME	DATE
UNLESS OTHERWISE SPECIFIED:							
DIMENSIONS ARE IN INCHES							
TOLERANCES:							
FRACTIONAL ±							
ANGULAR: MACH ± BEND ±							
TWO PLACE DECIMAL ±							
THREE PLACE DECIMAL ±							
INTERPRET GEOMETRIC TOLERANCING PER:							
MATERIAL							
FINISH							
DO NOT SCALE DRAWING							
PROPRIETARY AND CONFIDENTIAL THE INFORMATION CONTAINED IN THIS DRAWING IS THE PROPERTY OF SOLIDWORKS CORPORATION. ANY REPRODUCTION OR TRANSMISSION OF THIS DRAWING WITHOUT THE WRITTEN PERMISSION OF SOLIDWORKS CORPORATION IS PROHIBITED. <b>SolidWorks Student Edition.</b> <b>For Academic Use Only</b> * ASSY <INSERT COMPANY NAME HERE> IS USED ON APPLICATION							
SIZE DWG. NO. REV <b>Airt 8 1 8TH vert</b> SCALE: 1:2 WEIGHT: SHEET 1 OF 1							





## CIMWD-122 Syllabus

### *Gas Tungsten Arc Welding – Steel & Stainless Steel, Vertical*

#### ***Welding Procedure Specification***

WPS Name	CIMWD-122 Project 6
----------	---------------------

Weld Type	Fillet
Welding Process	GTAW
Position	Vertical
Material	1/8" Stainless Steel
Joint Type	Tee
Backing Option	
Backing Material	

Polarity	DC+
Electrode	308
Transfer Mode	
Tungsten Electrode	2% Ceriated
Shielding Gas	100% Argon
Flow Rate	25 cfh
Cup Size	

#### ***Welding Procedure***

Weld Layers	Pass No.	Process	Filler Metal Classification	Filler Metal Diameter in (mm)	Current Amps	Current Type and Polarity	Wire Feed Speed	Volts	Remarks
Stringer	Tee	GTAW	308	1/16"	75a	DC+			

<p>Technique: Butt Joint single pass weld in vertical up</p>
--





---

## **CIMWD-122 Syllabus**

### *Gas Tungsten Arc Welding – Steel & Stainless Steel, Vertical*

---

Heat Treatment:

Preheat Temperature-

Post Heat Temperature-

Interpass Temperature-

Stress Relieving-

Additional Notes:

Show the instructor progress every 30 minutes minimum.





---

## **CIMWD-122 Syllabus**

### *Gas Tungsten Arc Welding – Steel & Stainless Steel, Vertical*

---

#### **SAFETY DISCLAIMER:**

M-SAMC educational resources are in no way meant to be a substitute for occupational safety and health standards. No guarantee is made to resource thoroughness, statutory or regulatory compliance, and related media may depict situations that are not in compliance with OSHA and other safety requirements. It is the responsibility of educators/employers and their students/employees, or anybody using our resources, to comply fully with all pertinent OSHA, and any other, rules and regulations in any jurisdiction in which they learn/work. M-SAMC will not be liable for any damages or other claims and demands arising out of the use of these educational resources. By using these resources, the user releases the Multi-State Advanced Manufacturing Consortium and participating educational institutions and their respective Boards, individual trustees, employees, contractors, and sub-contractors from any liability for injuries resulting from the use of the educational resources.

#### **DOL DISCLAIMER:**

This product was funded by a grant awarded by the U.S. Department of Labor's Employment and Training Administration. The product was created by the grantee and does not necessarily reflect the official position of the U.S. Department of Labor. The Department of Labor makes no guarantees, warranties, or assurances of any kind, express or implied, with respect to such information, including any information on linked sites and including, but not limited to, accuracy of the information or its completeness, timeliness, usefulness, adequacy, continued availability, or ownership.

#### **RELEVANCY REMINDER:**

M-SAMC resources reflect a shared understanding of grant partners at the time of development. In keeping with our industry and college partner requirements, our products are continuously improved. Updated versions of our work can be found here: <http://www.msamc.org/resources.html>.

